

# 材料特性一览表

## MAGNETIC PROPERTIES OF MATERIALS

## EMI 材料特性表

## EMI Material Characteristics

特性 Characteristics 材料 Materials	初始磁导率 Initial Permeability $\mu_{iac}$ ( $\pm 25\%$ )	饱和磁通密度 Saturation Magnetic Flux Density Bs (mT)	剩磁 Residual Flux Density Br (mT)	矫顽力 Coercive Force Hc (A/m)	居里温度 Curie Temperature Tc ( $^{\circ}\text{C}$ )	应用频率 Recommended Frequency Range(MHz)
83(Ni-Zn)	650	290	150	22	>140	20~500
M93(Mn-Zn)	4000	300	150	10	>105	0.5~30
94(Ni-Zn)	125	320	120	60	>200	500~1000

所列材料的特性为该材料的典型值，测定样环：T25×15×8(mm)

The value of material's characteristics is typical value. Sample core: T25×15×8(mm)

## 镍锌铁氧体材料特性表

## NiZn Ferrite Material Characteristics

特性 Characteristics 材料 Materials	初始磁导率 Initial Permeability $\mu_{iac}$	比损耗因子 Relative Loss Factor $\tan\delta/\mu_{iac}$ ( $10^{-6}$ )	比温度系数 Relative Temperature Coefficient $\alpha\mu\gamma(10^{-6}/^{\circ}\text{C})$ 20—60 $^{\circ}\text{C}$	饱和磁通密度 Saturation Magnetic Flux Density Bs (mT)	矫顽力 Coercivity Hc (A/m)	居里温度 Curie Temperature Tc ( $^{\circ}\text{C}$ )	电阻率 Electrical Resistivity $\rho$ ( $\Omega\cdot\text{m}$ )	密度 Density d( $\text{g}/\text{cm}^3$ )
62	280	23 (0.1MHz)	6—17	500 (H=8000A/m)	21	>300	$10^6$	5.2
64	400	19 (0.1MHz)	3—16	430 (H=4000A/m)	26	>200	$10^6$	5.2
64L	400	30 (1.0MHz)	10—20	460 (H=4000A/m)	32	>230	$10^6$	5.2
64F	380	24 (1.0MHz)	5—17	450 (H=4000A/m)	28	>210	$10^6$	5.2
68	800	18 (0.1MHz)	8—17	350 (H=4000A/m)	24	>150	$10^6$	5.2
610	1000	15 (0.1MHz)	5—15	350 (H=4000A/m)	15	>140	$10^6$	5.2
620	2000	10 (0.2MHz)	3—6	300 (H=4000A/m)	16	>100	$10^6$	5.2
83	650	15 (0.1MHz)	4—18	290 (H=4000A/m)	22	>140	$10^6$	4.7
94	125	10 (0.2MHz)	8—17	300 (H=4000A/m)	60	>200	$10^6$	5.1

所列材料的特性为该材料的典型值，测定样环：T25×15×8(mm)

The value of material's characteristics is typical value. Sample core: T25×15×8(mm)

# 材料特性一览表

## MAGNETIC PROPERTIES OF MATERIALS





### 62 材料特性曲线

### 62 Material Characteristics Curve

特性 Characteristics	初始磁导率 Initial Permeability $\mu_{iac}$	比损耗因子 Relative Loss Pactor $\tan\delta/\mu_{iac} (10^{-6})$	比温度系数 Relative Temperature Coefficient $\alpha\mu\gamma(10^{-6}/^{\circ}\text{C})$ 20—60 $^{\circ}\text{C}$	饱和磁通密度 Saturation Magnetic Flux Density $B_s$ (mT)	矫顽力 Coercivity $H_c$ (A/m)	居里温度 Curie Temperature $T_c$ ( $^{\circ}\text{C}$ )	电阻率 Electrical Resistivity $\rho$ ( $\Omega\cdot\text{m}$ )	密度 Density $d(\text{g}/\text{cm}^3)$
62	280	23 (0.1MHz)	6—17	500 (H=8000A/m)	21	>300	$10^6$	5.2

所列材料的特性为该材料的典型值，测定样环：T25×15×8(mm)

The value of material's characteristics is typical value. Sample core: T25×15×8(mm)



# 材料特性一览表 MAGNETIC PROPERTIES OF MATERIALS





## 64 材料特性曲线

### 64 Material Characteristics Curve

特性 Characteristics	初始磁导率 Initial Permeability $\mu_{iac}$	比损耗因子 Relative Loss Pactor $\tan\delta/\mu_{iac} (10^{-6})$	比温度系数 Relative Temperature Coefficient $\alpha\mu\gamma(10^{-6}/^{\circ}\text{C})$ 20—60 $^{\circ}\text{C}$	饱和磁通密度 Saturation Magnetic Flux Density $B_s$ (mT)	矫顽力 Coercivity $H_c$ (A/m)	居里温度 Curie Temperature $T_c$ ( $^{\circ}\text{C}$ )	电阻率 Electrical Resistivity $\rho$ ( $\Omega\cdot\text{m}$ )	密度 Density $d(\text{g}/\text{cm}^3)$
64	400	19 (0.1MHz)	3—16	430 (H=4000A/m)	26	>200	$10^6$	5.2

所列材料的特性为该材料的典型值，测定样环：T25×15×8(mm)

The value of material's characteristics is typical value. Sample core: T25×15×8(mm)



# 材料特性一览表

## MAGNETIC PROPERTIES OF MATERIALS





### 64L 材料特性曲线

### 64L Material Characteristics Curve

特性 Characteristics	初始磁导率 Initial Permeability $\mu_{iac}$	比损耗因子 Relative Loss Pactor $\tan\delta/\mu_{iac} (10^{-6})$	比温度系数 Relative Temperature Coefficient $\alpha\mu\gamma(10^{-6}/^{\circ}\text{C})$ 20—60 $^{\circ}\text{C}$	饱和磁通密度 Saturation Magnetic Flux Density $B_s$ (mT)	矫顽力 Coercivity $H_c$ (A/m)	居里温度 Curie Temperature $T_c$ ( $^{\circ}\text{C}$ )	电阻率 Electrical Resistivity $\rho$ ( $\Omega\cdot\text{m}$ )	密度 Density $d(\text{g}/\text{cm}^3)$
64L	400	30 (1.0MHz)	10—20	460 (H=4000A/m)	32	>230	$10^6$	5.2

所列材料的特性为该材料的典型值，测定样环：T31×19×8(mm)

The value of material's characteristics is typical value. Sample core: T31×19×8(mm)



# 材料特性一览表

## MAGNETIC PROPERTIES OF MATERIALS





### 64F 材料特性曲线

### 64F Material Characteristics Curve

特性 Characteristics  材料 Materials	初始磁导率 Initial Permeability $\mu_{iac}$	比损耗因子 Relative Loss Factor $\tan\delta/\mu_{iac} (10^{-6})$	比温度系数 Relative Temperature Coefficient $\alpha\mu\gamma(10^{-6}/^{\circ}\text{C})$ 20—60°C	饱和磁通密度 Saturation Magnetic Flux Density $B_s$ (mT)	矫顽力 Coercivity $H_c$ (A/m)	居里温度 Curie Temperature $T_c$ (°C)	电阻率 Electrical Resistivity $\rho$ ( $\Omega\cdot\text{m}$ )	密度 Density $d(\text{g}/\text{cm}^3)$
64F	380	24 (0.1MHz)	5—17	450 (H=4000A/m)	28	>210	$10^6$	5.2

所列材料的特性为该材料的典型值，测定样环：T31×19×8(mm)

The value of material's characteristics is typical value. Sample core: T31×19×8(mm)



# 材料特性一览表

## MAGNETIC PROPERTIES OF MATERIALS





### 68 材料特性曲线

### 68 Material Characteristics Curve

特性 Characteristics	初始磁导率 Initial Permeability $\mu_{iac}$	比损耗因子 Relative Loss Pactor $\tan\delta/\mu_{iac} (10^{-6})$	比温度系数 Relative Temperature Coefficient $\alpha\mu\gamma(10^{-6}/^{\circ}\text{C})$ 20—60 $^{\circ}\text{C}$	饱和磁通密度 Saturation Magnetic Flux Density $B_s$ (mT)	矫顽力 Coercivity $H_c$ (A/m)	居里温度 Curie Temperature $T_c$ ( $^{\circ}\text{C}$ )	电阻率 Electrical Resistivity $\rho$ ( $\Omega\cdot\text{m}$ )	密度 Density $d(\text{g}/\text{cm}^3)$
68	800	18 (0.1MHz)	8—17	350 ( $H=4000\text{A}/\text{m}$ )	24	>150	$10^6$	5.2

所列材料的特性为该材料的典型值，测定样环：T25×15×8(mm)

The value of material's characteristics is typical value. Sample core: T25×15×8(mm)



# 材料特性一览表

## MAGNETIC PROPERTIES OF MATERIALS





### 610 材料特性曲线

### 610 Material Characteristics Curve

特性 Characteristics	初始磁导率 Initial Permeability $\mu_{iac}$	比损耗因子 Relative Loss Pactor $\tan\delta/\mu_{iac} (10^{-6})$	比温度系数 Relative Temperature Coefficient $\alpha\mu\gamma(10^{-6}/^{\circ}\text{C})$ 20—60 $^{\circ}\text{C}$	饱和磁通密度 Saturation Magnetic Flux Density $B_s$ (mT)	矫顽力 Coercivity $H_c$ (A/m)	居里温度 Curie Temperature $T_c$ ( $^{\circ}\text{C}$ )	电阻率 Electrical Resistivity $\rho$ ( $\Omega\cdot\text{m}$ )	密度 Density $d(\text{g}/\text{cm}^3)$
610	1000	15 (0.1MHz)	5—15	350 ( $H=4000\text{A}/\text{m}$ )	15	>140	$10^6$	5.2

所列材料的特性为该材料的典型值，测定样环：T25×15×8(mm)

The value of material's characteristics is typical value. Sample core: T25×15×8(mm)



# 材料特性一览表 MAGNETIC PROPERTIES OF MATERIALS





## 620 材料特性曲线

### 620 Material Characteristics Curve

特性 Characteristics	初始磁导率 Initial Permeability $\mu_{iac}$	比损耗因子 Relative Loss Pactor $\tan\delta/\mu_{iac} (10^{-6})$	比温度系数 Relative Temperature Coefficient $\alpha\mu\gamma(10^{-6}/^{\circ}\text{C})$ 20—60 $^{\circ}\text{C}$	饱和磁通密度 Saturation Magnetic Flux Density $B_s$ (mT)	矫顽力 Coercivity $H_c$ (A/m)	居里温度 Curie Temperature $T_c$ ( $^{\circ}\text{C}$ )	电阻率 Electrical Resistivity $\rho$ ( $\Omega\cdot\text{m}$ )	密度 Density $d(\text{g}/\text{cm}^3)$
620	2000	10 (0.2MHz)	3—6	300 (H=4000A/m)	16	>100	$10^6$	5.2

所列材料的特性为该材料的典型值，测定样环：T25×15×8(mm)

The value of material's characteristics is typical value. Sample core: T25×15×8(mm)





# 材料特性一览表

## MAGNETIC PROPERTIES OF MATERIALS





### 83 材料特性曲线

### 83 Material Characteristics Curve

特性 Characteristics 材料 Materials	初始磁导率 Initial Permeability $\mu_{iac}$	比损耗因子 Relative Loss Factor $\tan\delta/\mu_{iac} (10^{-6})$	比温度系数 Relative Temperature Coefficient $\alpha\mu\gamma(10^{-6}/^{\circ}\text{C})$ 20~60 $^{\circ}\text{C}$	饱和磁通密度 Saturation Magnetic Flux Density $B_s$ (mT)	矫顽力 Coercivity $H_c$ (A/m)	居里温度 Curie Temperature $T_c$ ( $^{\circ}\text{C}$ )	电阻率 Electrical Resistivity $\rho$ ( $\Omega\cdot\text{m}$ )	密度 Density $d(\text{g}/\text{cm}^3)$
83	650	15 (0.1MHz)	4—18	290 (H=4000A/m)	22	>140	$10^6$	4.7

所列材料的特性为该材料的典型值，测定样环：T25×15×8(mm)

The value of material's characteristics is typical value. Sample core: T25×15×8(mm)



# 材料特性一览表

## MAGNETIC PROPERTIES OF MATERIALS

### 94 材料特性曲线

### 94 Material Characteristics Curve

特性 Characteristics  材料 Materials	初始磁导率 Initial Permeability $\mu_{iac}$	比损耗因子 Relative Loss Factor $\tan\delta/\mu_{iac} (10^{-6})$	比温度系数 Relative Temperature Coefficient $\alpha\mu\gamma(10^{-6}/^{\circ}\text{C})$ 20—60 $^{\circ}\text{C}$	饱和磁通密度 Saturation Magnetic Flux Density $B_s$ (mT)	矫顽力 Coercivity $H_c$ (A/m)	居里温度 Curie Temperature $T_c$ ( $^{\circ}\text{C}$ )	电阻率 Electrical Resistivity $\rho$ ( $\Omega\cdot\text{m}$ )	密度 Density $d(\text{g}/\text{cm}^3)$
94	125	10 (0.2MHz)	8—17	300 (H=4000A/m)	60	>200	$10^6$	5.1

所列材料的特性为该材料的典型值，测定样环：T25×15×8(mm)

The value of material's characteristics is typical value. Sample core: T25×15×8(mm)

